

Technical Data Sheet

01th of January 2020
Version: 5.5

KRONOSPAN-MOFA Hungary Kft.
7700 Mohács • Hungary • Budapesti út 72.
Tel.: +36 69 529 511 • Fax.: +36 69 529 539
kronospan-mofa@kronospan-mofa.hu
www.kronospan-mofa.hu

Raw Thin HDF unsanded

Applications and uses:

Packaging, FCPM, Door industry, Furniture industry, Lacquering-, Laminating-, Mounting-, Finish foil-, Sandwich panel lines and any special



Characteristics:

Two faces of our RAW BOARD: THIN HDF are unsanded, homogeneous, closed and smooth.

If the order refers one or more variant about the next special requirements, we can offer all qualities below with CARB Phase 2 & US. EPA TSCA Title VI or GPCO (what is mean German Prohibition of Chemical Ordinance ([GermanVerbsotV; 01.01.2020](#))); combination with FSC Controlled Wood or PEFC Controlled Source and the FSC or PEFC MIX Credit certificate and/or difference GSoC in acc. to IOS-MAT std's. Following qualities can be lacquered with our lacquering line: EXPR, PLUS, DOOR. However, the standard lacquered quality that we propose is with "PLUS" base board.

Sign	Characteristics	Control standards	Unit	Thickness range (mm)					
				2,0 - 2,5	> 2,5 - 4,0	> 4,0 - 6,0	> 6,0 - 8,0		
t	Thickness tolerance	EN 324-1	mm	± 0,2					
lwt	Length/Width tolerance	EN 324-1	mm/m	± 2,0 (max.: ±5,0 mm)					
Sqt	Squareness tolerance	EN 324-2	mm/m	± 2,0					
St	Straightness	EN 324-2	mm/m	max.: 1,5					
D	Density	EN 323	kg/m ³	820 (LITE)					
				840 (EXPR)					
				855 (PLUS)					
				870 (DOOR; GPCO - 20203)					
Dt	Density tolerance	EN 323	%	±7					
Mc	Moisture content	EN 322	w/w %	4,0 – 11,0					
TSW	Thickness Swelling - 24 h	EN 317	w/w %	45	35	30	17		
BS	Bending strength	EN 310	N/mm ²	25 (LITE)					
				30 (EXPR)					
				35 (PLUS)		40 (PLUS)			
				40 (DOOR)		45 (DOOR)			
MOE	Modulus of elasticity	EN 310	N/mm ²	-					
				3 000 (EXPR)					
				3 300 (PLUS)		3 500 (PLUS)		4 000 (PLUS)	
				3 800 (DOOR)		4 000 (DOOR)		4 400 (DOOR)	
IB	Internal Bond	EN 319	N/mm ²	0,65 (LITE)					
				0,65 (EXPR)		0,70 (EXPR)		0,65 (EXPR)	
				0,75 (PLUS)					
				0,8 (DOOR)		0,9 (DOOR)		1,4 (DOOR)	
SS	Surface soundness	EN 311	N/mm ²	0,65 (LITE)					
				0,8 (EXPR)					
				1,2 (PLUS)					
				1,3 (DOOR)		1,5 (DOOR)			
Sta	Surface (Toluene) adsorption	EN 382-1	mm	150-300					
A-value	Surface (Water) adsorption	EN 382-2	g/m ²	300-600					
Sc	Sand (grit) content	ISO 3340	w/w %	max.: 0,05					
HCHO	Formaldehyde content & emissions (Please see the difference GSoC's!)								
PV	Perforator-value	EN ISO 12460-5:2015	mg/100g @6,5%MC	≤8,0 (E1)					
				≤5,0 (CARB Phase 2 – TSCA/EPA – E-LE)					
CTE	Chamber test-1	EN 717-1:2005	mg/m ³	≤0,124 (E1)					
				≤0,05 (GPCO - 20203)					
CTG	Chamber test-2	EN 16516:2017	ppm	≤0,1 (GPCO - 20203)					
CTA	Chamber test-3	ASTM E 1333-14 or ASTM D 6007-14	ppm	≤0,11 (CARB – TSCA/EPA – E-LE)					

(##): in brackets, the quality concerned ... If nothing specified, the parameter values are applicable for all the qualities.

Herewith we certify that our raw goods (unsanded thin HDF) comply with EN 622-1 and with EN 622-5 norm Table 3 – Requirements for general purpose boards for use dry conditions.

Recommendations:

HDF produced by KRONOSPAN-MOFA Hungary Ltd. should be stored in an area dry, temperate, ventilated and protected from the weather. If the storage is in an area with a high content of humidity or at low temperatures or very high, the stabilization of the board before its use is recommended (temperature and humidity of the workshop). If finish foil process is used, we recommend heating the board before the application of the adhesive and the paper. The edges of the full-size board must be sawed (clean cut). For specific applications, it is preferable to carry out preliminary tests.